

m/s Victoria Carpets Co Pty Ltd
7-29 Gladstone Rd, Dandenong Vic 3175
Attn Mr Matt Ilott

TEST REPORT No. 125896D

LABORATORY REF: P125896D

CUSTOMER REFERENCE
CITY LIVING PLUSH

Sample description as provided by customer
Mass/unit area **26 oz/yd² 880 g/m²**
Construction Details **Tufted** Secondary Backing **Jute**
Style **Cut Pile**

Order No. **4048740**
Pile Fibre Content **50% WOOL 50% POLYPROPYLENE**
Colour **Fawn**
Pile Height **6.0 mm**

TEST METHOD AS/ISO 9239.1 2003 Reaction To Fire Tests For Floorings Part 1 Determination of the Burning Behaviour Using a Radiant Heat Source. As required by specification C1.10a of the Building Code of Australia.

The test values relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product. Clause 9 of AS/ISO 9239 Part 1.

Conditioning as specified in BS EN 13238.2001

Sample submitted Date **Nov 2012**

Test Date **Feb 2013**

ASSEMBLY SYSTEM: OVER UNDERLAY AIRSTEP STEPEZY

The UNDERLAY used was **AIRSTEP STEPEZY**.

Substrate: Non-Combustible

Substrate - 6mm Fibre Reinforced Cement Board to simulate a Non-Combustible Flooring.

The Holding Torque on Specimen Frame was 2Nm.

Initial Test Specimen 1 Length Direction Critical Radiant Flux **2.8 kW/m²**
Specimen 1 Width Direction Critical Radiant Flux **2.6 kW/m²**
Full tests carried out in the **Width** Direction

SPECIMEN	Width #1	Width #2	Width #3	Mean
Critical Radiant Flux (kW/m ²)	2.6	2.5	2.8	2.6
Smoke Development Rate (%.min)	236	228	231	232

The values quoted below are as required by Specification C1.10a Fire Hazard Properties (Floors) of the Building Code of Australia. The Critical Radiant Flux quoted is the value at Flame-Out/Extinguishment (BCA General Provisions A1.1).

MEAN CRITICAL RADIANT FLUX 2.6 kW/m²

MEAN SMOKE DEVELOPMENT RATE 232 percent-minutes

OBSERVATIONS: The samples singed, ignited and burnt a relatively short distance.



M. B. Webb
Technical Manager

DATE: 5/2/2013

ACCREDITED FOR
TECHNICAL
COMPETENCE

Measurement Science &
Technology No. 15393
Accredited for compliance with ISO/IEC 17025.

PAGE 1 of 2

This Page (1) has been designed to show the values required under Specification C1.10a Fire Hazard Properties (Floors) of the Building Code of Australia.

The values on Page 2 have no relevance to the Code.

1004 04 09